

**Manufacturers and Distributors of Top Quality Paints and Solvents**

P.O. BOX 1633  
RANDBURG  
2125  
SOUTH AFRICA

PHONE: 027 11 864-1301/1302  
027 11 864-1036/1393  
FAX: 027 11 864-1390  
WEB SITE: [www.bandr.co.za](http://www.bandr.co.za)  
E-MAIL : [bandr@icon.co.za](mailto:bandr@icon.co.za)

Director: B. J. Rodd

**PRODUCT DATA SHEET  
GP RED OXIDE PRIMER**

<b><u>PRODUCT NAME:</u></b>	GENERAL PURPOSE INDUSTRIAL PRIMER RED OXIDE
<b><u>FINISH:</u></b>	MATT
<b><u>VEHICLE TYPE:</u></b>	ALKYD
<b><u>PIGMENT TYPE:</u></b>	SYNTHETIC IRON OXIDE
<b><u>SOLVENT TYPE:</u></b>	AROMATIC HYDROCARBONS
<b><u>FLASH POINT MIN:</u></b>	22°C
<b><u>SPECIFIC GRAVITY:</u></b>	1.200 – 1.250 AT 25°C
<b><u>SOLIDS CONTENT:</u></b>	60 – 65% BY WEIGHT
<b><u>VISCOSITY AT 25°C:</u></b>	650 cPu
<b><u>DRYING TIME:</u></b>	<b><u>SURFACE:</u></b> 15 – 30 MINUTES
	<b><u>HARD:</u></b> 2 – 3 HOURS
<b><u>APPLICATION METHOD:</u></b>	BRUSH OR CONVENTIONAL SPRAY
<b><u>APPLICATION VISCOSITY:</u></b>	BRUSH: READY FOR USE CONVENTIONAL SPRAY: 18 – 20 FC4
<b><u>RECOMMENDED THINNER:</u></b>	ENAMEL THINNERS
<b><u>FINENESS OF GRIND:</u></b>	10 MICRONS
<b><u>COVERAGE AT DFT 40 MICRONS:</u></b>	8 SQUARE METRES PER LITRE
<b><u>RECOMMENDED DRY FILM THICKNESS:</u></b>	40 MICRONS

**DESCRIPTION & GENERAL USE:**

A general purpose industrial primer for use on bare mild steel or galvanized iron for temporary protection against corrosion before finishing coats are applied. This product is not intended as a heavy duty anti-corrosive primer nor as a finishing coat on its own, but should be overcoated within six months of application.

All equipment must be cleaned immediately after use with enamel thinners.