

Manufacturers and Distributors of Top Quality Paints and Solvents

P.O. BOX 1633
RANDBURG
2125
SOUTH AFRICA

PHONE: 027 11 864-1301/1302
027 11 864-1036/1393
FAX: 027 11 864-1390
WEB SITE: www.bandr.co.za
E-MAIL : bandr@icon.co.za

Director: B. J. Rodd

**PRODUCT DATA SHEET
STOEP ENAMEL**

<u>PRODUCT NAME:</u>	ALKYD BASED FLOOR PAINT – STOEP ENAMEL
<u>FINISH:</u>	HIGH GLOSS
<u>COLOUR:</u>	RED, GREEN, GREY AND BLACK
<u>VEHICLE TYPE:</u>	MEDIUM LONG OIL ALKYD AND HARD PETROLEUM RESIN
<u>PIGMENT TYPE:</u>	ORGANIC AND INORGANIC PHTHALOCHROME
<u>SOLVENT TYPE:</u>	ALIPHATIC AND AROMATIC HYDROCARBONS
<u>FLASH POINT MIN:</u>	18°C
<u>SPECIFIC GRAVITY:</u>	1.050 – 1.150 AT 25°C
<u>SOLIDS CONTENT:</u>	60 – 75% BY WEIGHT
<u>VISCOSITY AT 25°C:</u>	800 - 850 cPu
<u>DRYING TIME:</u>	<u>SURFACE:</u> 2 – 4 HOURS
	<u>HARD:</u> 8 – 12 HOURS
<u>APPLICATION METHOD:</u>	BRUSH OR ROLLER
<u>FINENESS OF GRIND:</u>	5 – 10 MICRONS
<u>COVERAGE AT DFT 30 MICRONS:</u>	6 SQUARE METRES PER LITRE
<u>RECOMMENDED DRY FILM THICKNESS:</u>	30 - 40 MICRONS MIN PER COAT

DESCRIPTION & GENERAL USE:

A top quality alkyd floor coating for use on clean, grease and dust free concrete or stone floors. No primer is necessary on new surfaces but a bonding liquid may be applied to reduce initial absorption into porous surfaces.

All equipment must be cleaned immediately after use with mineral turpentine or enamel thinners.