

B & R PRODUCTS (PTY) LTD

Supreme Paint Suppliers (Pty) Ltd

Reg. No. 80/09849/07

Manufacturers and Distributors of Top Quality Paints and Solvents

P.O. BOX 1633
RANDBURG
2125
SOUTH AFRICA

PHONE: 027 11 864-1301/1302
027 11 864-1036/1393
FAX: 027 11 864-1390
WEB SITE: www.bandr.co.za
E-MAIL : bandr@icon.co.za

Director: B. J. Rodd

PRODUCT DATA SHEET CLEAR LACQUER

<u>PRODUCT NAME:</u>	LACQUER CLEAR
<u>FINISH:</u>	FULL GLOSS
<u>COLOUR:</u>	CLEAR
<u>VEHICLE TYPE:</u>	ALKYD NITROCELLULOSE
<u>PIGMENT TYPE:</u>	INORGANIC AND ORGANIC PHTHALOCHROMES
<u>SOLVENT TYPE:</u>	AROMATIC AND ALIPHATIC HYDROCARBONS, ESTERS, KETONES AND ALCOHOLS
<u>FLASH POINT MIN:</u>	-4°C
<u>SPECIFIC GRAVITY:</u>	0.900 – 1.090 AT 25°C MIXED
<u>SOLIDS CONTENT:</u>	35 – 40% BY WEIGHT MIXED
<u>THINNING RATIO:</u>	+ - 1 TO 1 BY VOLUME
<u>RECOMMENDED THINNER:</u>	B&R LACQUER THINNER
<u>VISCOSITY OF BASE AT 25°C:</u>	850 - 900 cpu
<u>DRYING TIME:</u>	<u>SURFACE:</u> 5 MINUTES AT 25°C
	<u>HARD:</u> 30 MINUTES AT 25°C
<u>APPLICATION METHOD:</u>	CONVENTIONAL SPRAY OR AIRLESS SPRAY.
<u>APPLICATION VISCOSITY:</u>	CONVENTIONAL GUN OR PRESSURE POT: 18 – 20" FORD CUP 4
<u>FINENESS OF GRIND:</u>	10 MICRONS
<u>RECOMMENDED PRIMER:</u>	SANDING SEALER
<u>RECOMMENDED DRY FILM THICKNESS:</u>	20 – 30 MICRONS PER COAT

DESCRIPTION & GENERAL USE:

A top quality nitrocellulose lacquer for use on all wooden surfaces as well as for general industrial use on steel. The product must be used in a well-ventilated area only.

Automotive Lacquer continued/...

PRODUCT SAFETY DATA

FLASH POINT	:	<5°C
HIGHLY FLAMMABLE	:	Always store in a cool place. If set alight, use only powder fire extinguishers.
SKIN CONTACT	:	Wash immediately with lots of soap and water
EYE CONTACT	:	Rinse with lots of water and seek medical attention as soon as possible.
IF INGESTED	:	Do not induce vomiting. Seek medical attention immediately.