

B & R PRODUCTS (PTY) LTD

Supreme Paint Suppliers (Pty) Ltd

Reg. No. 80/09849/07

Manufacturers and Distributors of Top Quality Paints and Solvents

P.O. BOX 1633
RANDBURG
2125
SOUTH AFRICA

PHONE: 027 11 864-1301/1302
027 11 864-1036/1393
FAX: 027 11 864-1390
WEB SITE: www.bandr.co.za
E-MAIL : bandr@icon.co.za

Director: B. J. Rodd

PRODUCT DATA SHEET Q.D. ANTI CORROSIVE ENAMEL

<u>PRODUCT NAME:</u>	QUICK DRYING ANTI CORROSIVE ENAMEL
<u>PRODUCT BRAND:</u>	SUPREME
<u>FINISH:</u>	GLOSS
<u>COLOURS:</u>	VARIOUS COLOURS
<u>VEHICLE TYPE:</u>	STYRENATED ALKYD
<u>PIGMENT TYPE:</u>	ZINC PHOSPHATE, INORGANIC PIGMENTS CHROMATES AND ORGANIC PHTHALOCHROMES
<u>SOLVENT TYPE:</u>	AROMATIC HYDROCARBONS
<u>FLASH POINT MIN:</u>	22°C
<u>SPECIFIC GRAVITY:</u>	0.950 – 1.010 AT 25°C
<u>SOLIDS CONTENT:</u>	50 – 55% BY WEIGHT
<u>DENSITY:</u>	1,09 Kg/litre
<u>VISCOSITY AT 25°C:</u>	90" FC4
<u>DRYING TIME:</u>	<u>SURFACE:</u> 10 – 15 MINUTES
	<u>HARD:</u> 1 – 2 HOURS
<u>APPLICATION METHOD:</u>	SPRAY OR DIP
<u>APPLICATION VISCOSITY:</u>	CONVENTIONAL SPRAY: 18 – 20" FC4
<u>RECOMMENDED THINNER:</u>	Q.D ENAMEL THINNERS
<u>FINENESS OF GRIND:</u>	5 MICRONS
<u>GLOSS:</u>	85% ON 60°
<u>HEAT RESISTANCE:</u>	250 – 300 DEGREES C
<u>COVERAGE AT DFT 40 MICRONS:</u>	5 SQUARE METRES PER LITRE
<u>RECOMMENDED DRY FILM THICKNESS:</u>	40 MICRONS

DESCRIPTION & GENERAL USE:

A quick drying general-purpose industrial enamel with anti-corrosive pigments for use as a primer topcoat all in one. Can be sprayed directly onto steel or alloys without a primer. All surfaces must be clean and dry.

All equipment must be cleaned immediately after use with thinners.

