

# B & R PRODUCTS (PTY) LTD

*Supreme Paint Suppliers (Pty) Ltd*

Reg. No. 80/09849/07

**Manufacturers and Distributors of Top-Quality Paints and Solvents**

P.O. BOX 1633  
RANDBURG  
2125  
SOUTH AFRICA

PHONE: 027 11 864-1301/1302  
027 11 864-1036/1393  
FAX: 027 11 864-1390  
WEB SITE: [www.bandr.co.za](http://www.bandr.co.za)  
E-MAIL : [bandr@icon.co.za](mailto:bandr@icon.co.za)

Director: B. J. Rodd

## PRODUCT DATA SHEET STOEP ENAMEL

<b><u>PRODUCT NAME:</u></b>	<b>ALKYD BASED FLOOR PAINT – STOEP ENAMEL</b>
<b><u>FINISH:</u></b>	HIGH GLOSS
<b><u>COLOUR:</u></b>	VAROUS COLOURS
<b><u>VEHICLE TYPE:</u></b>	MEDIUM LONG OIL ALKYD AND HARD PETROLEUM RESIN
<b><u>PIGMENT TYPE:</u></b>	INORGANIC AND ORGANIC PHTHALOCHROME
<b><u>SOLVENT TYPE:</u></b>	ALIPHATIC AND AROMATIC HYDROCARBONS
<b><u>FLASH POINT MIN:</u></b>	18°C
<b><u>SPECIFIC GRAVITY:</u></b>	1.050 – 1.150 AT 25°C
<b><u>SOLIDS CONTENT:</u></b>	60 – 70% BY WEIGHT
<b><u>VISCOSITY AT 25°C:</u></b>	800 - 850 cPu
<b><u>DRYING TIME:</u></b>	<b><u>SURFACE:</u></b> 2 - 4 HOURS
	<b><u>HARD:</u></b> 8 – 12 HOURS
<b><u>APPLICATION METHOD:</u></b>	BRUSH OR ROLLER
<b><u>FINENESS OF GRIND:</u></b>	5 - 10 MICRONS
<b><u>COVERAGE AT DFT 30 MICRONS:</u></b>	6 SQUARE METRES PER LITRE
<b><u>RECOMMENDED DRY FILM THICKNESS:</u></b>	30 - 40 MICRONS MIN PER COAT

### **DESCRIPTION & GENERAL USE:**

A top quality alkyd floor coating for use on clean, grease and dust free concrete or stone floors.

All grease, oil or any other contaminant must also be completely removed using either an industrial degreaser or a 50:50 solution of pool acid and water to etch into the floor. Once dried, all loose concrete and dust must be removed. It is also recommended that this be done for new floors too.

All equipment must be cleaned immediately after use with mineral turpentine or enamel thinners.

