

B & R PRODUCTS (PTY) LTD

Supreme Paint Suppliers (Pty) Ltd

Reg. No. 80/09849/07

Manufacturers and Distributors of Top Quality Paints and Solvents

P.O. BOX 1633
RANDBURG
2125
SOUTH AFRICA

PHONE: 027 11 864-1301/1302
027 11 864-1036/1393
FAX: 027 11 864-1390
WEB SITE: www.bandr.co.za
E-MAIL : bandr@icon.co.za

Director: B. J. Rodd

PRODUCT DATA SHEET SUPER EGGSHELL ENAMEL

| | |
|---|---|
| <u>PRODUCT NAME:</u> | SUPER EGGSHELL ENAMEL |
| <u>PRODUCT BRAND:</u> | SUPREME |
| <u>FINISH:</u> | SATIN |
| <u>COLOUR:</u> | WHITE AND PASTEL TINTS |
| <u>VEHICLE TYPE:</u> | MEDIUM OIL ALKYD |
| <u>PIGMENT TYPE:</u> | INORGANIC |
| <u>SOLVENT TYPE:</u> | ALIPHATIC AND AROMATIC HYDROCARBONS |
| <u>FLASH POINT MIN:</u> | 18°C |
| <u>SPECIFIC GRAVITY:</u> | 1.150 – 1.175 AT 25°C |
| <u>SOLIDS CONTENT:</u> | 60 – 70% BY WEIGHT |
| <u>VISCOSITY AT 25°C:</u> | 800 - 850 cPu |
| <u>DRYING TIME:</u> | <u>SURFACE:</u> 2 HOURS |
| | <u>HARD:</u> 6 – 8 HOURS |
| <u>OVERCOATING TIME:</u> | MIN 6 HOURS AT 25 DEGREES CELSIUS |
| <u>APPLICATION METHOD:</u> | BRUSH, ROLLER OR CONVENTIONAL SPRAY |
| <u>APPLICATION VISCOSITY:</u> | BRUSH OR ROLLER: READY FOR USE CONVENTIONAL SPRAY: 18 – 20 FC4 |
| <u>RECOMMENDED THINNER:</u> | ENAMEL THINNERS |
| <u>FINENESS OF GRIND:</u> | 5 - 10 MICRONS |
| <u>COVERAGE AT DFT 30 MICRONS:</u> | 6 SQUARE METRES PER LITRE (DEPENDING ON SURFACE PROFILE) |
| <u>RECOMMENDED DRY FILM THICKNESS:</u> | 30 - 40 MICRONS |

DESCRIPTION & GENERAL USE:

A top quality brushing, alkyd enamel for interior and exterior household use on all types of firm, clean substrates. Wood and metals should be primed with the appropriate primer and given a coat of supreme universal undercoat before applying the enamel topcoat. Cement, plaster and brickwork should first be sealed with supreme bonding liquid and allowed to dry for 6 – 8 hours.

All equipment must be cleaned immediately after use with turps or enamel thinners.