

B & R PRODUCTS (PTY) LTD

Supreme Paint Suppliers (Pty) Ltd

Reg. No. 80/09849/07

Manufacturers and Distributors of Top Quality Paints and Solvents

P.O. BOX 1633
RANDBURG
2125
SOUTH AFRICA

PHONE: 027 11 864-1301/1302
027 11 864-1036/1393
FAX: 027 11 864-1390
WEB SITE: www.bandr.co.za
E-MAIL : bandr@icon.co.za

Director: B. J. Rodd

PRODUCT DATA SHEET SUPER HIGH GLOSS ENAMEL

<u>PRODUCT NAME:</u>	SUPER HIGH GLOSS ENAMEL
<u>PRODUCT BRAND:</u>	SUPREME
<u>FINISH:</u>	HIGH GLOSS
<u>COLOUR:</u>	BLACK, WHITE AND STANDARD COLOURS
<u>VEHICLE TYPE:</u>	MEDIUM OIL ALKYD
<u>PIGMENT TYPE:</u>	INORGANIC AND ORGANIC PHTHALOCHROME
<u>SOLVENT TYPE:</u>	ALIPHATIC AND AROMATIC HYDROCARBONS
<u>FLASH POINT MIN:</u>	18°C
<u>SPECIFIC GRAVITY:</u>	1.050 – 1.150 AT 25°C
<u>SOLIDS CONTENT:</u>	60 – 70% BY WEIGHT
<u>VISCOSITY AT 25°C:</u>	800 - 850 cPu
<u>DRYING TIME:</u>	<u>SURFACE:</u> 2 HOURS
	<u>HARD:</u> 6 – 8 HOURS
<u>OVERCOATING TIME:</u>	MIN 6 HOURS AT 25 DEGREES CELSIUS
<u>APPLICATION METHOD:</u>	BRUSH, ROLLER OR CONVENTIONAL SPRAY
<u>APPLICATION VISCOSITY:</u>	BRUSH OR ROLLER: READY FOR USE CONVENTIONAL SPRAY: 18 – 20 FC4
<u>RECOMMENDED THINNER:</u>	TURPS / ENAMEL THINNERS
<u>FINENESS OF GRIND:</u>	5 - 10 MICRONS
<u>COVERAGE AT DFT 30 MICRONS:</u>	6 SQUARE METRES PER LITRE
<u>SHELF LIFE:</u>	12 MONTHS
<u>RECOMMENDED DRY FILM THICKNESS:</u>	30 - 40 MICRONS

DESCRIPTION & GENERAL USE:

A top quality brushing, alkyd enamel for interior and exterior use, on all types of firm, clean substrates. Wood and metals should be primed with the appropriate primer and given a coat of supreme universal undercoat before applying the enamel topcoat. Cement, plaster and brickwork should first be sealed with supreme bonding liquid and allowed to dry for 6 – 8 hours.

All equipment must be cleaned immediately after use with turps or enamel thinners.